







## Leadfree Solder Wires (with Silver content) available from us, normally with immediate delivery


Stannol Germany provides wide range of highest quality Solder Wires for different types of soldering applications.

Solder Wires can be flux-cored or solid. The flux is necessary for the soldering process to remove oxidation and other impurities to guarantee a reliable solder joint. Flux-cored Solder Wires already contain the correct amount of flux. Different fluxes are used depending on the soldering tasks.

Halide-free Solder Wire Fluxes are used if halides are not permitted in the manufacturing process and if higher electrical safety of the residues is required.

STANNOL® Leadfree Solder Wires in HF32 series are high quality flux cored types. Activated & halide-free flux, meets DIN EN 29454 type 1.1.3 and IEC 61190-1-3 type ROL0 standard. Flux residues are solid and dry, and are not corrosive when tested in accordance with DIN 8516.

The halide-free Solder Wires with flux HF32 have good wetting characteristics and leave low residues on the circuit boards.



An important part of the solder wires is flux, which is responsible for the removal of oxidation from the metal surfaces. The Stannol range includes solder wires with 1 and 5 flux cores.



**Lead Free Soldering Wire** Sn95Ag4Cu1, 0.3mm, 250g **Ordering No.: 631970** 



**Lead Free Soldering Wire** Sn95Ag4Cu1, 0.5mm, 500g **Ordering No.: 631962** 



**Lead Free Soldering Wire** Sn95Ag4Cu1, 0.7mm, 500g **Ordering No.: 631967** 



**Lead Free Soldering Wire** Sn95Ag4Cu1,1.0mm, 500g **Ordering No.: 631974** 

STANNOL® HF32 are recommended for use in both robotic soldering and hand-soldering. For manual soldering, temperature controlled Soldering Stations only should be used to prevent excessive heat being applied. Flux spatter from the formulation is fairly low. STANNOL® Solder Wire HF32 meets the requirements of DIN 8516, with respect to surface insulation resistance and electromigration. Flux residues are not corrosive to non-ferrous metals.

General Properties	Leadfree Solder Wires with Silver HF32 series
Composition	Sn95.5, Ag3.8, Cu0.7
Flux type	standard 3.5% ± 0.3 %
Halide content	none, according to DIN EN ISO 9455-6
Corrosion effect	none, according to DIN EN 29455-5 and -15
Available spool type	0.3mm in 250gms and others in 500gms